

\* NOTICES \*

JPO and INPIT are not responsible for any damages caused by the use of this translation.

- 1.This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.\*\*\*\* shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

---

CLAIMS

---

[Claim(s)]

[Claim 1]Anti-dazzle material which has a surface roughening layer which comes to distribute a filler in a resin matrix at least via direct or other layers to one side or both sides of a transparent substrate, and is characterized by a difference of a refractive index of this resin matrix and a filler being 0.10 or less.

[Claim 2]The anti-dazzle material according to claim 1 in which particle size distribution of the particle diameter D of said filler is characterized by a thing of a range whose thing of a range whose things of the range of  $0.5 \leq D \leq 6.0$  micrometers are 60 % of the weight or more and  $6.0 < D \leq 10.0$  micrometers is  $10 < D \leq 15.0$  micrometers further less than 30% of the weight being 5 or less % of the weight.

[Claim 3]A surface roughening layer which comes to distribute a filler is provided into a resin matrix at least via direct or other layers at one side of a transparent substrate, A polarization film in which a surface roughening layer of this transparent substrate has the composition which laminates a protective layer via a polarization base to an opposite side, and a difference of a refractive index of said resin matrix and a filler is characterized by being 0.10 or less.

---

[Translation done.]